



SPECIFICATION

**NAME : ALMIT SRC Solder Paste
Sn62 (Ag2) HM1-RMA V14L 12% Flux**

Lot No.	Marketing Name
	Sn62 (Ag2) HM1-RMA V14L Flux content 12% Solder Powder Size: 25-45µm (Type 3)

NIHON ALMIT Co. Ltd.

Head Office: Almit Bldg., 2-14-2, Yayoicho, Nakano-ku, Tokyo
164, **Japan.** Tel: 03-3379-2277 Fax: 03-3374-2593

Almit Technology Ltd: Unit 7, Forest Row Business Park, Station Road,
Forest Row, East Sussex. RH18 5DW
England
Tel: +44(0)1342 822 844 Fax: +44(0)1342 824 155

Almit GmbH: FloBerstrasse 56, D-74321, Bietigheim-Bissingen,
Germany
Tel: +49(0)7142 773327 Fax: +49(0)7142 773335

Venso Elektronik AB: Ogardesvagen 21, SE-433 30 Partille, **Sweden**
Tel: +46(0)31 3400250 Fax: +46(0)31 3400275

1. **Product Name:** Sn62 (Ag2) HM1-RMA V14L 12% Flux

2. **Scope:** This specification is specified for Almit solder paste Sn62 (Ag2) HM1-RMA V14L 12% Flux delivered by Nihon Almit Co, Ltd to Messrs. _____

3. **Weight and Tolerances: (g)**

Weight	40	100
Allowance	+ 2, - 0	+ 5, - 0

4. **Chemical Composition: (wt. %) (QQ-S-571F)**

Sn62 (Ag2) HM1-RMA V14L 12% Flux

Compo.	Sn	Pb	Ag	Sb	Cu	Bi	Zn	Fe
Sn62	61.5/62.5	Bal	1.8/2.2	≤ 0.12	≤ 0.08	≤ 0.1	≤ 0.005	≤ 0.02

Al	As	Cd	Au	In	Ni	P	Other
≤ 0.005	≤ 0.03	≤ 0.005	≤ 0.08	≤ 0.1	≤ 0.01	≤ 0.01	≤ 0.005

5. **Solder Powder Size & Distribution:**

Size (μm) 25/45	Powder Size (μm)	+ 45	- 20
	Distribution (wt %)	≤ 5.0	≤ 1.0

6. **Characteristics:**

Items	Characteristics	Test Methods
Flux Content (wt %)	12.0 +/- 0.5	JIS-Z-3197
Halides (Chloride & Bromide)	Pass	QQ-S-571F
Water Extract Resistance (Ω/cm)	≥ 100,000	QQ-S-571F
Cu Mirror Test	Pass	QQ-S-571F
SIR (Ω)	≥ 1 x 10 ¹²	JIS-Z-3197
Spreadability on Cu Plate (%)	≥ 80	JIS-Z-3197
Cu Plate Corrosion Test	Pass	JIS-Z-3284
Dryness	Pass	JIS-Z-3197
Flux Type	L1	J-STD-0004

7. **Physical Properties:**

Sn62 (Ag2) HM1-RMA V14L 12% Flux

Solidus Degs C	Liquidus Degs C	Specific Gravity
179	179	8.4

8. Construction of one Lot:

Manufactured in lots of between 10kg and 100kg depending on order requirement.

9. Quality & Inspection.

Inspection criteria are applied to each lot as follows :-

Item No.	Inspection Item		
1	Appearance	Colour	Comparison with Limit Specimen
2	Weight	Net Weight	- 0 , + 2 or 5 (g)
3	Solder Powder Size	25/45	≥ 90 (wt. %)
4	Metal Composition	Sn (Sn62)	62.0 +/- 0.5 (wt %)
		Pb & Impurities	Rest
		Ag (Ag2)	2.0 +/- 0.2 (wt%)
5	Characteristics	Flux Content	12.0 +/- 0.5 (wt %)
6		Solder Balling Test (* Nihon Almit Method)	Comparison with limit specimen
7		Viscosity (S Type, 10 rpm , 25 ^o C)	40~150 (Pa.s)
8		Solderability on Cu Plate	Comparison with limit specimen
9		Dryness	Chalk powder should be easily removed from each specimen.

NB. *

Straight lines of solder paste are printed onto a JIS-2 type PCB then reflowed. The reflowed solder is examined with a stereo microscope at 30x magnification. No more than two solder balls larger than one fifth the size of the pattern gap is allowed per gap.

10. Packaging:

Sn62 (Ag2) HM1-RMA V14L 12% Flux

Individual Packaging		Outer Packaging	
Unit	Packaging	Unit	Packaging
25 g	5 cc syringe	250g	Cardboard Box
40g	10 cc syringe	400g	Cardboard Box
100g	30 cc syringe	1 kg	Cardboard Box

11. Identification:

Sn62 (Ag2) HM1-RMA V14L 12% Flux

	Syringe	Cardboard box
Name	Almit SRC Solder Paste Sn62 (Ag2) HM1-RMA V14L 12% Flux	Same as Polyethylene bottle
Sn Content	Indicate " Sn62 " in the product name	Ditto
Ag Content	Indicate " Ag2 " in the product name	Ditto
Lot No.	(Example) 970324-1	Ditto
Solder Powder Size	25 - 45 μ m	Ditto
Date of Mfg.	(Example) 97 - 03 - 24 *	Ditto
Validation Date	(Example) 09 - 23 **	Ditto
Weight (Nett)	(Example) 100 g	Ditto
Company Name	Nihon Almit Co. Ltd.	Ditto

NB * Date is shown as Year (97) Month (03) Day (24)

** Date is shown as Month (06) Day (23) This Date is usually 6 months after Mfg. Date.

12. Makers Address:

Nihon Almit Co. Ltd.

Almit Bldg. , 2-14-2 Yayoicho, Nakano-ku, Tokyo, 164, JAPAN.

13. Changes to this specification must be approved by:-

Signed _____ Date _____

HANDLING PROCEDURES FOR ALMIT Sn62 (Ag2) HM1-RMA V14L 12% FLUX SOLDER PASTE

1) STORAGE

Unopened containers should be kept in a refrigerator at 3 to 8 Degs C.

Paste should be used as soon as possible after the container has been opened.

Keep the container **sealed as much as possible** to reduce contamination and oxidation.

2) USAGE

Before screening/dispensing, the paste must be allowed to reach room temperature, this may take up to 8 hours dependant on volume.

After the paste has reached room temperature remove the lid and stir slowly using a stainless steel spatula. Try to avoid trapping air in the paste as much as possible thus keeping oxidation to a minimum.

After screening/dispensing, components may be placed (mounted) immediately and passed straight into the reflow oven. See also Almit Solder Paste Reflow Parameters Data Sheet.

The paste is designed for no clean assembly but post reflow residues may be cleaned if required by customers specifications. Almit can advise on suitable cleaning processes.

At the end of the batch/shift any used paste **may** be discarded, however, to minimise wastage without any loss of performance **ALMIT** recommend that any paste remaining on the screen is carefully removed and stored in a clean airtight pot, (a spare ALMIT pot is ideal) mark the pot with the specification of the paste and store overnight in a refrigerator if required. During the next batch/shift this paste may be used to **supplement** the **fresh paste** added throughout the day, care being taken to ensure the specifications of both pastes are identical and the paste has reached room temperature.

Any residual paste on the screen or squeegee should be removed using a recommended solvent or Alcohol.

3) ADDITIONAL INFORMATION

The Solder paste contains **LEAD**.

Ingestion, contact with eyes and skin must be avoided at all times using normal Health & Safety procedures. i.e.: Rubber gloves.

The Solder paste must only be used for industrial use under controlled conditions by trained operators.

Avoid inhalation of any process gasses. To be used in a properly ventilated area.

4) HEALTH & SAFETY NOTICE

Any solder paste on the skin must be removed at once with Alcohol followed by washing with detergent and warm water.

The use of Goggles and Gloves is strongly recommended.

Reference should also be made to the **ALMIT COSHH** documentation.

5) DELIVERY

The product is held in stock in the UK, hence delivery in the UK is usually within 3 working days of receipt of an order.